

Page 1 of 24



TEST REPORT IEC 62133-2

Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications – Part 2: Lithium systems

Report Number:	LCSA122122002S
Date of issue:	2023-02-15
Total number of pages:	24 pages
Applicant's name:	Shenzhen Hongshengze Energy Technology Co., Ltd.
Address:	Room 401, Floor 4, Building A, Hongzan printing company, District A, Longquan Industrial Zone, HengLang community,DaLang Street, LongHua District ,Shenzhen City, Guangdong, P.R.China
Test specification:	
Standard:	IEC 62133-2:2017, IEC 62133-2:2017/AMD1:2021
Test procedure:	Type Test
Non-standard test method:	N/A
TRF template used:	IECEE OD-2020-F1:2021, Ed.1.4
Test Report Form No:	IEC62133_2C
Test Report Form(s) Originator:	DEKRA Certification B.V.
Master TRF:	Dated 2022-07-01

Copyright © 2017 IEC System of Conformity Assessment Schemes for Electro technical Equipm Components (IECEE System). All rights reserved.

This publication may be reproduced in whole or in part for non-commercial purposes as long as the IECEE is acknowledged as co owner and source of the material. IECEE takes no responsibility for and will not assume liability for damages resulting from the reinterpretation of the reproduced material due to its placement and context.

General disclaimer:

The test results presented in this report relate only to the object tested.

This report shall not be reproduced, except in full, without the written approval of Shenzhen LCS Compliance Testing Laboratory Ltd. The authenticity of this Test Report and its contents can be verified by contacting the Shenzhen LCS Compliance Testing Laboratory Ltd., responsible for this Test Report.

Test item description:	Li-ion Battery
Trade Mark:	N/A
Manufacturer:	Dongguan Hongshengze Energy Technology Co., Ltd. Floor 5, building 4, No.66, South Fifth Street, Qiaodong Road, Dongjiang Village, Qiaotou Town, Dongguan City,Guangdong, P.R.China
Model/Type reference:	HSZ 350820 - TinyCircuits ASR00072
Ratings:	3.7V, 40mAh, 0.148Wh



Responsible Testing Laboratory (as applicable), testing procedure and testing location(s):



\boxtimes	Testing Laboratory:	Shenzhen LCS Complia	ance Testing Laboratory Ltd.
Testing	location/ address:		g A and Room 301, Building C, ianxueziwei, Shajing Street, en, Guangdong, China
Tested	by (name, signature)::	Heisen Liu	Heisen in
Checke	ed by(name, signature):	Dean Du	Deanstu
Approv	ved by (name, signature):	Hart Qiu	PEROSE
	Testing procedure: CTF Stage 1:		
Testing	location/ address:		
Tested	by (name, function, signature):		
Approv	ved by (name, function, signature):		
1 H 10	Testing procedure: CTF Stage 2:	Till the total	g Lab
Testing	location/ address:	The Local Park	152 100 100
Tested	by (name + signature):		
Witnes	sed by (name, function, signature).:		
Approv	ved by (name, function, signature):		
	Testing procedure: CTF Stage 3:		
	Testing procedure: CTF Stage 4:	-ciis	in.US
Testing	location/ address:	A Testing Lab	THE LOS Testing Lab
Tested	by (name, function, signature):		
Witnessed by (name, function, signature).:			
Approv	red by (name, function, signature) :		
Superv	rised by (name, function, signature) :		





Attachment 1: Photo Documentation (4 pages).

Summary of testing:

Tests performed (name of test and test clause):

- cl.7.1 Charging procedure for test purposes (for Cells and Batteries);
- cl.7.2.1 Continuous charging at constant voltage (Cells);
- cl.7.2.2 Case stress at high ambient temperature (Batteries);
- cl.7.3.1 External short-circuit (Cells);
- cl.7.3.2 External short-circuit (Batteries);
- cl.7.3.3 Free fall (Cells and Batteries);
- cl.7.3.4 Thermal abuse (Cells);
- cl.7.3.5 Crush (Cells);
- cl.7.3.6 Over-charging of battery;
- cl.7.3.7 Forced discharge (Cells);
- cl.7.3.8 Mechanical tests (Batteries);
- cl.7.3.9 Design evaluation Forced internal short-circuit (cells).

Tests are made with the number of cells and batteries specified in IEC 62133-2:2017, IEC62133-2:2017/ AMD1:2021 Table 1.

Testing location:

Shenzhen LCS Compliance Testing Laboratory Ltd.

Room 101, 201, Building A and Room 301, Building C, Juji Industrial Park, Yabianxueziwei, Shajing Street, Bao'an District, Shenzhen, Guangdong, China

Summary of compliance with National Differences (List of countries addressed): N/A

☐ The product fulfils the requirements of EN 62133-2:2017, EN 62133-2:2017/AMD1:2021 and BS EN 62133-2:2017+A1:2021

Use of uncertainty of measurement for decisions on conformity (decision rule):

No decision rule is specified by the IEC standard, when comparing the measurement result with the applicable limit according to the specification in that standard. The decisions on conformity are made without applying the measurement uncertainty ("simple acceptance" decision rule, previously known as "accuracy method").

Other:... (to be specified, for example when required by the standard or client, or if national accreditation requirements apply)

Information on uncertainty of measurement:

The uncertainties of measurement are calculated by the laboratory based on application of criteria given by OD-5014 for test equipment and application of test methods, decision sheets and operational procedures of IECEE.

IEC Guide 115 provides guidance on the application of measurement uncertainty principles and applying the decision rule when reporting test results within IECEE scheme, noting that the reporting of the measurement uncertainty for measurements is not necessary unless required by the test standard or customer.

Calculations leading to the reported values are on file with the NCB and testing laboratory that conducted the testing.





Copy of marking plate:

The artwork below may be only a draft. The use of certification marks on a product must be authorized by the respective NCBs that own these marks.

> Red (+) Black (-)

Li-ion Battery

Model: HSZ 350820 3.7V, 40mAh, 0.148Wh

1ICP4/8/20 YYYY/MM/DD

Dongguan Hongshengze Energy Technology Co., Ltd.

WARNING:

Do not disassemble, puncture, crush, heat, or burn.

Remark:

1. "YYYY" means year for manufacture;

"MM" means month for manufacture;

"DD" means day for manufacture.

2.The applicant and manufacturer information, product name, model, trademark and other information in this report are all provided by the applicant, and this laboratory is not responsible for verifying its authenticity.







	1.0: 1.0: 1.0:	
Test item particulars:	VIST CS Testing Law	VIST UCS Testi
Classification of installation and use:	To be defined in final product	The same
Supply Connection:	DC connector	
Recommend charging method declared by the manufacturer:	Charging the battery with 8mA const 4.2V constant voltage until the curre 0.8mA at ambient 20°C±5°C	
Discharge current (0,2 lt A):	8mA	
Specified final voltage:	3.0V	
Upper limit charging voltage per cell:	4.2V	
Maximum charging current:	40mA	
Charging temperature upper limit:	45°C	
Charging temperature lower limit:	0°C	
Polymer cell electrolyte type:	☐ gel polymer ☐ solid polymer	⊠ N/A
Possible test case verdicts:		
- test case does not apply to the test object:	N/A	
- test object does meet the requirement:	P (Pass)	
- test object does not meet the requirement:	F (Fail)	
Testing:	10000000000000000000000000000000000000	- 40 711
Date of receipt of test item:	2022-12-21	
Date (s) of performance of tests:	2022-12-21 to 2023-01-09	
General remarks:		
The test results presented in this report relate only to the o This report shall not be reproduced, except in full, without t		ng laboratory.
"(See Enclosure #)" refers to additional information apper "(See appended table)" refers to a table appended to the refers to a table appended to table appended		
Throughout this report a $\ \ \ \ \ \ \ \ \ \ \ \ \ $	ed as the decimal separator.	(分别服务
Manufacturer's Declaration per sub-clause 4.2.5 of IEC	EEE 02:	Testing Lab
The application for obtaining a CB Test Certificate includes more than one factory location and a declaration from the Manufacturer stating that the sample(s) submitted for evaluation is (are) representative of the products from each factory has been provided:	☐ Yes ☑ Not applicable	
When differences exist; they shall be identified in the 0	General product information section	l.
Name and address of factory (ies)	Same as the manufacturer	







General product information and other remarks:

This battery is constructed with one li-ion cell in 1S1P, and has overcharge, over-discharge, over current and short-circuits proof circuit.

The main features of the battery are shown as below (clause 7.1.1):

Model	Nominal capacity	Nominal voltage	Nominal Charge Current	Nominal Discharge Current	Maximum Charge Current	Maximum Discharge Current	Maximum Charge Voltage	Cut-off Voltage
HSZ 350820	40mAh	3.7V	8mA	8mA	40mA	40mA	4.2V	3.0V

The main features of the cell in the battery are shown as below (clause 7.1.1):

Model	Nominal capacity	Nominal voltage	Nominal Charge Current	Nominal Discharge Current	Maximum Charge Current	Maximum Discharge Current	20 F C2	Cut-off Voltage
350820	40mAh	3.7V	8mA	8mA	40mA	40mA	4.2V	3.0V

The main features of the cell in the battery are shown as below (clause 7.1.2):


	Model	Upper limit charge voltage	Taper-off current	Lower charge temperature	Upper charge temperature
ĺ	350820	4.2V	2mA	0°C	45°C






Shenzhen LCS Compliance Testing Laboratory Ltd.
Add: 1-2F, Building A&3F, Building C, Juji Industrial Park, Yabianxueziwei, Shajing Street, Bao'an District, Shenzhen, Guangdong, China














4	PARAMETER MEASUREMENT TOLERANCES		Р
	Parameter measurement tolerances		Р

5	GENERAL SAFETY CONSIDERATIONS		Р
5.1	General		Р
	Cells and batteries so designed and constructed that they are safe under conditions of both intended use and reasonably foreseeable misuse		Р
5.2	Insulation and wiring	S4 mr	₩ P
医拉	The insulation resistance between the positive terminal and externally exposed metal surfaces of the battery (excluding electrical contact surfaces) is not less than $5~\mathrm{M}\Omega$	No metal surface exists.	N/A
	Insulation resistance (MΩ) :		_
	Internal wiring and insulation are sufficient to withstand maximum anticipated current, voltage and temperature requirements		Р
	Orientation of wiring maintains adequate clearances and creepage distances between conductors		Р
	Mechanical integrity of internal connections accommodates reasonably foreseeable misuse		Р
5.3	Venting	对位于111752	Р
	Battery cases and cells incorporate a pressure relief mechanism or are constructed so that they relieve excessive internal pressure at a value and rate that will preclude rupture, explosion and self-ignition	Venting mechanism exists on the narrow side of pouch cell.	Pes
	Encapsulation used to support cells within an outer casing does not cause the battery to overheat during normal operation nor inhibit pressure relief		N/A
5.4	Temperature, voltage and current management		Р
	Batteries are designed such that abnormal temperature rise conditions are prevented	Overcharge, over discharge, over current and short-circuit proof circuit used in this battery. See tests of clause 7.	P
TEL THE	Batteries are designed to be within temperature, voltage and current limits specified by the cell manufacturer	See above.	Р
	Batteries are provided with specifications and charging instructions for equipment manufacturers so that specified chargers are designed to maintain charging within the temperature, voltage and current limits specified	The charging limits specified in the manufacturer's specification.	Р
5.5	Terminal contacts		Р
	The size and shape of the terminal contacts ensure that they can carry the maximum anticipated current	DC connector complied with the requirements.	Р
立形检测股份 LCS Testing Lab	External terminal contact surfaces are formed from conductive materials with good mechanical strength and corrosion resistance	Complied.	P Liff fail CS Test



A TIME	IEC	62133-2	W. o
Clause	Requirement + Test	Result - Remark	Verdict

	Terminal contacts are arranged to minimize the risk of short circuits		Р
5.6	Assembly of cells into batteries		Р
5.6.1	General		Р
	Each battery has an independent control and protection for current, voltage, temperature and any other parameter required for safety and to maintain the cells within their operating region	Protective circuit equipped on battery.	Р
	This protection may be provided external to the battery such as within the charger or the end devices		N/A
	If protection is external to the battery, the manufacturer of the battery provide this safety relevant information to the external device manufacturer for implementation	LES TESTING	N/A
	If there is more than one battery housed in a single battery case, each battery has protective circuitry that can maintain the cells within their operating regions	Single cell battery.	N/A
	Manufacturers of cells specify current, voltage and temperature limits so that the battery manufacturer/designer may ensure proper design and assembly	Current, voltage and temperature limits specified by cell manufacturer.	Р
立讯检测股份 LCS Testing Lab	Batteries that are designed for the selective discharge of a portion of their series connected cells incorporate circuitry to prevent operation of cells outside the limits specified by the cell manufacturer	用位测度价 STasting Lab	N/A
	Protective circuit components are added as appropriate and consideration given to the end-device application		Р
	The manufacturer of the battery provide a safety analysis of the battery safety circuitry with a test report including a fault analysis of the protection circuit under both charging and discharging conditions confirming the compliance	Safety analysis report provided by manufacturer.	Р
5.6.2	Design recommendation		Р
ISA ILIS	For the battery consisting of a single cell or a single cellblock, it is recommended that the charging voltage of the cell does not exceed the upper limit of the charging voltage specified in Table 2	Max. charging voltage: 4.2V, not exceed 4.2V specified by manufacturer in Table 2.	P P
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks, it is recommended that the voltages of any one of the single cells or single cellblocks does not exceed the upper limit of the charging voltage, specified in Table 2, by monitoring the voltage of every single cell or the single cellblocks		N/A







Y	Page 11 of 24	Report No. LCSA122	1220023
是那能力	IEC 62133-2	10 10 10 10 10 10 10 10 10 10 10 10 10 1	- 1 THE SHIP
Clause	Requirement + Test	Result - Remark	Verdict
1000	121	152	Iron.
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks, it is recommended that charging is stopped when the upper limit of the charging voltage is exceeded for any one of the single cells or single cellblocks by measuring the voltage of every single cell or the single cellblocks		N/A
	For batteries consisting of series-connected cells or cell blocks, nominal charge voltage are not counted as an overcharge protection	- OP to	N/A
TE IT	For batteries consisting of series-connected cells or cell blocks, cells have closely matched capacities, be of the same design, be of the same chemistry and be from the same manufacturer	Los Testing	N/A
	It is recommended that the cells and cell blocks are not discharged beyond the cell manufacturer's specified final voltage	Final voltage of cell: 3.0V, not exceed the final voltage specified by cell manufacturer.	Р
	For batteries consisting of series-connected cells or cell blocks, cell balancing circuitry are incorporated into the battery management system		N/A
5.6.3	Mechanical protection for cells and components of batteries	- 115	Р
立形检测版的 LCSTesting La	Mechanical protection for cells, cell connections and control circuits within the battery are provided to prevent damage as a result of intended use and reasonably foreseeable misuse	Mechanical protection for cell connections and control circuits provided.	P. III
	The mechanical protection can be provided by the battery case or it can be provided by the end product enclosure for those batteries intended for building into an end product	Build-in batteries, mechanical protection for cells should be provided by end product.	N/A
	The battery case and compartments housing cells are designed to accommodate cell dimensional tolerances during charging and discharging as recommended by the cell manufacturer	To be evaluated in final system.	N/A
E TO	For batteries intended for building into a portable end product, testing with the battery installed within the end product is considered when conducting mechanical tests	LET 立流检测器	N/A
5.7	Quality plan		Р
	The manufacturer prepares and implements a quality plan that defines procedures for the inspection of materials, components, cells and batteries and which covers the whole process of producing each type of cell or battery	Complied. Quality plan provided.	Р
5.8	Battery safety components	See TABLE: Critical components information	N/A







Report No. LCSA122122002S



12 THE P. L.	份 公司服务	IEC 62133-2	A IIII - CA
Clause	Requirement + Test	Result - Remark	Verdict

6	TYPE TEST AND SAMPLE SIZE		Р
	Tests are made with the number of cells or batteries specified in Table 1 using cells or batteries that are not more than six months old		Р
	The internal resistance of coin cells are measured in accordance with Annex D. Coin cells with internal resistance less than or equal to 3 Ω are tested in accordance with Table 1	Not coin cells	N/A
	Unless otherwise specified, tests are carried out in an ambient temperature of 20 °C ± 5 °C	100	P
12	The safety analysis of 5.6.1 identify those components of the protection circuit that are critical for short-circuit, overcharge and over discharge protection	LCS Testing	(Эр Б
	When conducting the short-circuit test, consideration is given to the simulation of any single fault condition that is likely to occur in the protecting circuit that would affect the short-circuit test	See clause 7.3.2.	Р

7	SPECIFIC REQUIREMENTS AND TESTS		Р
7.1	Charging procedure for test purposes		Р
7.1.1	First procedure		Р
- 用检测股份	This charging procedure applies to subclauses other than those specified in 7.1.2	用控制股份	Р
LCS Testing	Unless otherwise stated in this document, the charging procedure for test purposes is carried out in an ambient temperature of 20 °C ± 5 °C, using the method declared by the manufacturer	See page 5.	LGS Pass
	Prior to charging, the battery has been discharged at 20 °C ± 5 °C at a constant current of 0,2 lt A down to a specified final voltage	See page 5.	Р
7.1.2	Second procedure		Р
	This charging procedure applies only to 7.3.1, 7.3.4, 7.3.5, and 7.3.9		Р
	After stabilization for 1 h to 4 h, at an ambient temperature of the highest test temperature and the lowest test temperature, respectively, as specified in Table 2, cells are charged by using the upper limit charging voltage and maximum charging current, until the charging current is reduced to 0,05 lt A, using a constant current to constant voltage charging method	Charge temperature 0~45°C declared. 45°C used for upper limit tests, 0°C used for lower limit tests.	P
7.2	Intended use		Р
7.2.1	Continuous charging at constant voltage (cells)	Tested complied.	Р
	Fully charged cells are subjected for 7 days to a charge using the charging method for current and standard voltage specified by the cell manufacturer	Charging for 7 days with 8mA.	Р
	Results: no fire, no explosion, no leakage :	(See appended table 7.2.1)	Р
7.2.2	Case stress at high ambient temperature (battery)	Tested as client requested.	Р
THE THE PARTY OF	Oven temperature (°C):	70°C	







10 全部 100	IEC 62133-2	(2) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1	1
Clause	Requirement + Test	Result - Remark	Verdict
FCD 1	104	Los and the same of the same o	FCo /
	Results: no physical distortion of the battery case resulting in exposure of internal protective components and cells	No physical distortion of the battery case.	Р
7.3	Reasonably foreseeable misuse		Р
7.3.1	External short-circuit (cell)	Tested complied.	Р
	The cells were tested until one of the following occurred:		Р
	- 24 hours elapsed; or		N/A
	- The case temperature declined by 20 % of the		Р
	maximum temperature rise		份
_ 10	Results: no fire, no explosion:	(See appended table 7.3.1)	rap B
7.3.2	External short-circuit (battery)	Tested complied.	Р
	The batteries were tested until one of the following occurred:		Р
	- 24 hours elapsed; or		Р
	- The case temperature declined by 20 % of the		Р
	maximum temperature rise		
	In case of rapid decline in short circuit current, the battery pack remained on test for an additional one		Р
	hour after the current reached a low end steady state condition		
115	A single fault in the discharge protection circuit is	Single fault conducted on four	Р
	conducted on one to four (depending upon the	samples.	可怜测
	protection circuit) of the five samples before	C. Lesting Lan	Trillia
	conducting the short-circuit test	152	ros
	A single fault applies to protective component parts	Single fault applies on	Р
	such as MOSFET (metal oxide semiconductor	MOSFET (U2) short circuit.	
	field-effect transistor), fuse, thermostat or positive		1/3
	temperature coefficient (PTC) thermistor		1/3
	Results: no fire, no explosion:	(See appended table 7.3.2)	₹
7.3.3	Free fall	Tested complied.	//Pik
	Results: no fire, no explosion	No fire. No explosion	P
7.3.4	Thermal abuse (cells)	Tested complied.	Р
	Oven temperature (°C):	130°C	_
	Results: no fire, no explosion	No fire. No explosion	Р
7.3.5	Crush (cells)	Tested complied.	Р
The In	The crushing force was released upon:	157 100	Р
	- The maximum force of 13 kN \pm 0,78 kN has been		Р
	applied; or		
	- An abrupt voltage drop of one-third of the original		N/A
	voltage has been obtained		
	Results: no fire, no explosion:	(See appended table 7.3.5)	Р
7.3.6	Over-charging of battery	Tested complied.	Р
	The supply voltage which is:		Р
	- 1,4 times the upper limit charging voltage presented in Table A.1 (but not to exceed 6,0 V) for single cell/cell block batteries or	5.88V applied.	Р







是問題的	IEC 62133-2	Report No. LOOA 12.	lim:
Clause	Requirement + Test	Result - Remark	Verdict
Co.	163 (03.	(2)	FC2 Jean
	- 1,2 times the upper limit charging voltage resented in Table A.1 per cell for series connected multi-cell batteries, and		N/A
	- Sufficient to maintain a current of 2,0 It A throughout the duration of the test or until the supply voltage is reached		Р
	Test was continued until the temperature of the outer casing:		Р
	- Reached steady state conditions (less than 10 °C change in 30-minute period); or		P 份
49	- Returned to ambient	· 田道	N/A
VISA 10	Results: no fire, no explosion:	(See appended table 7.3.6)	Р
7.3.7	Forced discharge (cells)	Tested complied.	Р
	Discharge a single cell to the lower limit discharge voltage specified by the cell manufacturer	Lower limit discharge voltage 3.0V.	Р
	The discharged cell is then subjected to a forced discharge at 1 It A to the negative value of the upper limit charging voltage		Р
可检测股份	- The discharge voltage reaches the negative value of upper limit charging voltage within the testing duration. The voltage is maintained at the negative value of the upper limit charging voltage by reducing the current for the remainder of the testing duration		N/A
LC5 Testing	- The discharge voltage does not reach the negative value of upper limit charging voltage within the testing duration. The test is terminated at the end of the testing duration	S Tastinu (15)	LOS Pesti
	Results: no fire, no explosion:	(See appended table 7.3.7)	Р
7.3.8	Mechanical tests (batteries)	- /	Р
7.3.8.1	Vibration	Tested complied.	Р
	Results: no fire, no explosion, no rupture, no leakage or venting.	(See appended table 7.3.8.1)	Р
7.3.8.2	Mechanical shock	Tested complied.	Р
	Results: no leakage, no venting, no rupture, no explosion and no fire :	(See appended table 7.3.8.2)	P
7.3.9	Design evaluation – Forced internal short-circuit (cells)	Tested complied.	Lab P
1154 10	The cells complied with national requirement for :	France, Japan, Korea, Switzerland	_
	The pressing was stopped upon:		Р
	- A voltage drop of 50 mV has been detected; or		N/A
	- The pressing force of 800 N (cylindrical cells) or 400 N (prismatic cells) has been reached	400N for prismatic cells.	P
	Results: no fire :	(See appended table 7.3.9)	Р

8	INFORMATION FOR SAFETY		Р
8.1	General		Р
To Barrer	Manufacturers of secondary cells provides	Information for safety	P
THE PROPERTY	information about current, voltage and temperature	mentioned in manufacturer's	17 10 1911
LCSTesting	limits of their products	specifications.	LCS Testin





IEC 62133-2			
Clause	Requirement + Test	Result - Remark	Verdict
100	155 100.	152	Fear
	Manufacturers of batteries provides information regarding how to minimize and mitigate hazards to equipment manufacturers or end-users	Information for safety mentioned in manufacturer's specifications.	P
	Systems analyses are performed by device manufacturers to ensure that a particular battery design prevents hazards from occurring during use of a product		N/A
	As appropriate, any information relating to hazard avoidance resulting from a system analysis is provided to the end user		N/A
VS T	Do not allow children to replace batteries without adult supervision	ITS TOTAL	N/A
8.2	Small cell and battery safety information	Small cells and batteries	Р
	The following warning language is to be provided with the information packaged with the small cells and batteries or equipment using them:	Information for safety mentioned in manufacturer's specifications.	Р
	- Keep small cells and batteries which are considered swallowable out of the reach of children		Р
	- Swallowing may lead to burns, perforation of soft tissue, and death. Severe burns can occur within 2 h of ingestion		Р
一色测度份	- In case of ingestion of a cell or battery, seek medical assistance promptly	4年刑股份	Р

9	MARKING		Р
9.1	Cell marking	The final product is battery	N/A
	Cells are marked as specified in IEC 61960, except coin cells		N/A
	Coin cells whose external surface area is too small to accommodate the markings on the cells show the designation and polarity		N/A
	By agreement between the cell manufacturer and the battery and/or end product manufacturer, component cells used in the manufacture of a battery need not be marked		N/A
9.2	Battery marking	Till Time	_{Fab} b
180	Batteries are marked as specified in IEC 61960, except for coin batteries	See marking plate on page 4.	Р
	Coin batteries whose external surface area is too small to accommodate the markings on the batteries show the designation and polarity	Not coin batteries.	N/A
	Batteries are marked with an appropriate caution statement	Batteries marked with an appropriate caution statement.	Р
	- Terminals have clear polarity marking on the external surface of the battery, or	The "+(Red)" and "-(Black)" polarity explicitly marked on surface of the battery.	Р





- A - TILL TO	IEC 62133-2	- 10 TIM 152 (77	W. O.
Clause	Requirement + Test	Result - Remark	Verdict
Too .	153 100	100	FC2 ;
	- Not be marked with polarity markings if the design of the external connector prevents reverse polarity connections	Special designed connector used. Also the connector construction designed wrong polarity insert prevented.	Р
9.3	Caution for ingestion of small cells and batteries		N/A
	Coin cells and batteries identified as small batteries include a caution statement regarding the hazards of ingestion in accordance with 8.2	Not coin cells and batteries.	N/A
- 11	Small cells and batteries are intended for direct sale in consumer-replaceable applications, caution for ingestion is given on the immediate package	Not intended for direct sale.	N/A
9.4	Other information	NSA (CSTES	Р
	The following information are marked on or supplied with the battery:	Information for storage and disposal instructions mentioned in manufacturer's specifications.	Р
	- Storage and disposal instructions		Р
	- Recommended charging instructions		Р

10	PACKAGING AND TRANSPORT		Р
	Packaging for coin cells are not be small enough to fit	Not coin cells.	N/A
- 12 m	within the limits of the ingestion gauge of Figure 3	- A. A.	

ANNEX A	CHARGING AND DISCHARGING RANGE OF SECONDARY LITHIUM ION CELLS FOR SAFE	CS Testing	LOS Pesti
	USE		
A.1	General		Р
A.2	Safety of lithium ion secondary battery	Complied.	Р
A.3	Consideration on charging voltage	Complied.	Р
A.3.1	General		Р
A.3.2	Upper limit charging voltage	4.2V applied.	Р
A.3.2.1	General		Р
A.3.2.2	Explanation of safety viewpoint		N/A
A.3.2.3	Safety requirements, when different upper limit charging voltage is applied	4.2V applied.	N/A
A.4	Consideration of temperature and charging current	157 LCS Testing	Р
A.4.1	General		Р
A.4.2	Recommended temperature range	See A.4.2.2.	Р
A.4.2.1	General		Р
A.4.2.2	Safety consideration when a different recommended temperature range is applied	Charging temperature declared by client is: 0~45°C	Р
A.4.3	High temperature range	Not higher than the temperature specific in this standard.	N/A
A.4.3.1	General		N/A
A.4.3.2	Explanation of safety viewpoint	1. ml 股份	N/A
A.4.3.3	Safety considerations when specifying charging conditions in the high temperature range	HARATING Land	N/A





177 BH 1111-11	IEC 62133-2	Neport No. 200A12	
Clause	Requirement + Test	Result - Remark	Verdict
LC2 Team	100 100 100	[C23,425]	rca (aa
A.4.3.4	Safety considerations when specifying a new upper limit in the high temperature range		N/A
A.4.4	Low temperature range	Charging low temperature declared by client is:.	Р
A.4.4.1	General		Р
A.4.4.2	Explanation of safety viewpoint		Р
A.4.4.3	Safety considerations, when specifying charging conditions in the low temperature range		Р
A.4.4.4	Safety considerations when specifying a new lower limit in the low temperature range	0°C applied.	P
A.4.5	Scope of the application of charging current	一 世界程 100	rap B
A.4.6	Consideration of discharge	155 105 188	Р
A.4.6.1	General		Р
A.4.6.2	Final discharge voltage and explanation of safety viewpoint		Р
A.4.6.3	Discharge current and temperature range		Р
A.4.6.4	Scope of application of the discharging current		Р
A.5	Sample preparation		Р
A.5.1	General		Р
A.5.2	Insertion procedure for nickel particle to generate internal short		Р
A.5.3	Disassembly of charged cell		Р
A.5.4	Shape of nickel particle	可怜7997	Р
A.5.5	Insertion of nickel particle in cylindrical cell	STESUNO US	N/A
A.5.5.1	Insertion of nickel particle in winding core		N/A
A.5.5.2	Marking the position of the nickel particle on both ends of the winding core of the separator		N/A
A.5.6	Insertion of nickel particle in prismatic cell		Р
A.6	Experimental procedure of the forced internal short-circuit test		Р
A.6.1	Material and tools for preparation of nickel particle		Р
A.6.2	Example of a nickel particle preparation procedure		Р
A.6.3	Positioning (or placement) of a nickel particle		Р
A.6.4	Damaged separator precaution		ıs P
A.6.5	Caution for rewinding separator and electrode	- 16 JUB	Р
A.6.6	Insulation film for preventing short-circuit	La Testini	Р
A.6.7	Caution when disassembling a cell	1	Р
A.6.8	Protective equipment for safety		Р
A.6.9	Caution in the case of fire during disassembling		Р
A.6.10	Caution for the disassembling process and pressing the electrode core		Р
A.6.11	Recommended specifications for the pressing device		Р
		- I	







Page 18 of 24

Report No. LCSA122122002S

V	Page 18 of 24 Report No. LCSA			
1 SI III - SA	IEC 62133-2	一种测度 加	W. Ser	
Clause	Requirement + Test	Result - Remark	Verdict	
T Cop .	1/25 rcs.	1137 res . H	P.Co.	
ANNEX B	RECOMMENDATIONS TO EQUIPMENT MAN	IUFACTURERS AND BATTERY	N/A	
	ASSEMBLERS			
ANNEX C	RECOMMENDATIONS TO THE END-USERS		N/A	

ANNEX D	MEASUREMENT OF THE INTERNAL AC RESISTANCE FOR COIN CELLS					
D.1	General	Not coin cells	N/A			
D.2	Method		N/A			
	A sample size of three coin cells is required for this measurement	(See appended table D.2)	N/A			
	Coin cells with an internal resistance of less than or equal to 3 Ω are subjected to the testing according to Clause 6 and Table 1		N/A			
	Coin cells with an internal resistance greater than 3 Ω require no further testing		N/A			

ANNEX E	PACKAGING AND TRANSPORT	N/A
		•
ANNEX F	COMPONENT STANDARDS REFERENCES	N/A









UST 立形位测度的





TABLE: Critical components information							
Object/part no.	Manufacturer/ trademark	Type/model Technical data			Mark(s) of conformity ¹⁾		
Cell	Shenzhen Hongshengze Energy Technology CO., LTD.	350820	3.7V, 40mAh	IEC 62133-2:201 7, IEC+A1	Tested with appliance		
- Positive Electrode	JiangMen KehengTechnol ogy Co., Ltd.	TE-510	LiCoO ₂ , NMP, PVDF, Conductive Additive, Aluminum Foil				
- Negative Electrode	Shanghai ShanShan Technology Co., Ltd.	LKP-G5	Graphite, CMC, SBR, Conductive Additive, Copper Foil	LOS TEN	sztiua rap		
- Electrolyte	DongGuang TianFeng PowerSuppiy MaterialsCo., Ltd	TF-009C	LiPF ₆ +EMC+EC+DEC				
- Separator	Shenzhen HangTaiYuang Technology Co., Ltd.	HTY-T-9+3	12μm, PP, Shutdown Temperature: 120°C				
Protection IC (U1)	Shenzhen Puolop Electronics Co., Ltd	DW01	Overcharge Protection Voltage: 4.28±0.05V, Over-discharge Protection Voltage: 2.4±0.1V, T _{opr} : -40°C~+85°C		Tested with appliance		
MOSFET (U2)	Shenzhen Puolop Electronics Co., Ltd	8205	V _{DS} :20V, V _{GS} : ±12V, I _D :6A, T _J : -55°C~+150°C		Tested with appliance		
PCB	SHENZHEN Aishengxin Electronic CO LTD	ASX-M	V-0, 130°C	UL 796	UL E187447		
Wire	DongGuan Cheng XingElectronic CO.,Ltd	1571	26AWG, 80°C, 30V	UL 758	UL E214382		



¹⁾ Provided evidence ensures the agreed level of compliance.

7.2.1	TABLE:	Continuous charging	g at constant voltage	(cells)	Р	
Sample	no.	Recommended charging voltage Vc (Vdc)	Recommended charging current I _{rec} (mA)	OCV before test (Vdc)	Resi	ılts
Cell #1		4.20	8	4.20	Р	
Cell #2	2	4.20	8	4.19	Р	
Cell #3	3	4.20	8	4.19	Р	
Cell #4	ļ	4.20	8	4.20	Р	
Cell #5		4.20	8	4.20	Р	16 E
Supplementar	y informa	ation:	THE Testing Lab	, III	立河福加 CS Testin	a Fap

- No fire or explosion
- No leakage

3.1	TAE	BLE: External short-	circuit (cells)			Р
Sample no.		Ambient T (°C)	$\begin{array}{c cccc} \text{OCV before} & \text{Resistance of} \\ \text{test (Vdc)} & \text{circuit (m}\Omega) & \text{temperature} \\ & & \text{rise } \Delta T, \text{ (°C)} \end{array}$		Results	
		Samples charged	l at charging ten	nperature upper l	imit (45°C)	
Cell #6		55.5	4.18	84	112.9	P
Cell #7		55.5	4.18	82	113.0	Р
Cell #8		55.5	4.18	88	115.7	Р
Cell #9		55.5	4.17	84	116.6	Р
Cell #10)	55.5	4.18	85	110.0	Р
		Samples charge	d at charging te	mperature lower	limit (0°C)	
Cell #11		55.8	4.12	86	110.8	Р
Cell #12		55.8	4.12	90	109.5	Р
Cell #13	检测	55.8	4.12	86	107.8	P
Cell #14	3 Tastin	55.8	4.11	87	115.4	Testing P
Cell #15	,	55.8	4.11	84	113.0	Р

- No fire or explosion







7.3.2	TABLE: External short-circuit (batteries)								
Sample no.	Ambient (°C)	OCV before test (Vdc)	Resistance of circuit (mΩ)	Maximum case temperature rise ∆T, (°C)	Component single fault condition	Results			
Battery #4	24.0	4.17	84	113.3	MOSFET (U2) Short circuit	Р			
Battery #5	24.0	4.18	80	105.5	MOSFET (U2) Short circuit	Р			
Battery #6	24.0	4.18	86	103.8	MOSFET (U2) Short circuit	服件P ing Lab			
Battery #7	24.0	4.17	79	108.9	MOSFET (U2) Short circuit	Р			
Battery #8	24.0	4.17	82	24.5		Р			

- No fire or explosion

5	TABLE	E: Crush (cells)			F
Samp	ole no.	OCV before test (Vdc)	OCV at removal of crushing force (Vdc)	Maximum force applied to the cell during crush (kN)	Results
	;	Samples charged at ch	arging temperature up	per limit (45°C)	
Cell	#29	4.17	4.17	13	Р
Cell	#30	4.18	4.18	13	Р
Cell	#31	4.17	4.17	13	Р
Cell	#32	4.18	4.18	13	Р
Cell	#33	4.17	4.17	13	Р
		Samples charged at ch	narging temperature lo	wer limit (0°C)	
Cell	#34	4.11	4.11	13	P
Cell	#35	4.11	4.11	13	Testing P
Cell	#36	4.12	4.12	13	Р
Cell	#37	4.11	4.11	13	Р
Cell	#38	4.11	4.11	13	Р

- No fire or explosion





6 T	TABLE: Over-charging of battery						
nstant charging current (A) 0.08							
pply voltage (Vdc)		:		5.88		_
Sample no. OCV before chargin (Vdc)			Total char	rging time lute)	Maximum outer case temperature (°C)	Re	esults
Battery #12		3.34	8	4	36.3		Р
Battery #13		3.35	8	4	34.5		Р
Battery #14		3.35	8	4	35.2		Р
Battery #15	测限	3.34	8	4	35.8	松那	Р
Battery #16	sting,	3.36	8	4	36.1	Testin	Р

No fire or explosion

7.3.7	TABLI	TABLE: Forced discharge (cells)							
Sample n	0.	OCV before application of reverse charge (Vdc)	Measured reverse charge I _t (mA)	Lower limit discharge voltage (Vdc)	Resu	Its			
Cell #39		3.34	80	3.0	Р				
Cell #40		3.35	80	3.0	Р	一田拉測			
Cell #41		3.34	80	3.0	P	LOS TEST			
Cell #42		3.35	80	3.0	Р				
Cell #43		3.33	80	3.0	Р				

Supplementary information:

Scan code to check authenticity

- No fire or explosion









7.3.8.1	TAB	LE: Vibration	Testing Lab	Presti		
Sample no	•	OCV before test (Vdc)	OCV after test (Vdc)	Mass before test (g)	Mass after test (g)	Results
Battery #17	7	4.18	4.17	1.326	1.323	Р
Battery #18	3	4.17	4.17	1.258	1.254	Р
Battery #19)	4.18	4.18	1.364	1.360	Р

- No fire or explosion
- No rupture
- No leakage
- No venting

7.3.8.2	TABLE: Mechanical shock							
Sample no.		OCV before test (Vdc)	OCV after test (Vdc)	Mass before test (g)	Mass after test (g)	Re	sults	
Battery #20		4.17	4.17	1.321	1.317		Р	
Battery #21		4.17	4.17	1.299	1.296		Р	
Battery #22		4.18	4.18	1.314	1.311		Р	

Supplementary information:

- No fire or explosion
- No rupture
- No leakage
- No venting









7.3.9 TABLE: Forced internal short circuit (cells)								
Sample no.	Chamber ambient T (°C)	OCV before test (Vdc)	Particle location ¹⁾	Maximum applied pressure (N)	Results			
Samples charged at charging temperature upper limit (45°C)								
Cell #44	45	4.17	1	400	Р			
Cell #45	45	4.18	1	400	Р			
Cell #46	45	4.18	1	400	Р			
Cell #47	45	4.18	股份 1	400	Р			
Cell #48	45	4.17	ng Lab 1	400	P			
	Samples charge	d at charging tem	perature lower li	mit (0°C)				
Cell #49	0	4.11	1	400	Р			
Cell #50	0	4.11	1	400	Р			
Cell #51	0	4.12	1	400	Р			
Cell #52	0	4.12	1	400	Р			
Cell #53	0	4.11	1	400	Р			

- 1: Nickel particle inserted between positive and negative (active material) coated area.
- 2: Nickel particle inserted between positive aluminium foil and negative active material coated area.
- No fire

D.2	TABLE:	TABLE: Internal AC resistance for coin cells					
Sample no.		Ambient T (°C)	Store time (h)	Resistance Rac (Ω)	Results 1)		
	- W 43		- 02 Hi				
Supplement	ary information	on:	T. H. Wing Lab	工 拉洲	Eing Lab		

-- End of Report --





¹⁾ Identify one of the following:

Photo Documentation



Page 1 of 4

Report No. LCSA122122002S

Li-ion Battery Product: HSZ 350820 Type Designation:




Figure 1 Front view of battery




Figure 2 Back view of battery



Shenzhen LCS Compliance Testing Laboratory Ltd.
Add: 1-2F, Building A&3F, Building C, Juji Industrial Park, Yabianxueziwei, Shajing Street, Bao'an District, Shenzhen, Guangdong, China

Photo Documentation



Page 2 of 4

Report No. LCSA122122002S

Li-ion Battery Product: HSZ 350820 Type Designation:




Figure 3 Internal view -1 of battery




Figure 4 Internal view -2 of battery



Photo Documentation



Page 3 of 4

Report No. LCSA122122002S

Li-ion Battery Product: HSZ 350820 Type Designation:




Figure 5 Front view of cell




Figure 6 Back view of cell



Photo Documentation



Page 4 of 4

Report No. LCSA122122002S

Product: Li-ion Battery

Type Designation: HSZ 350820




Figure 7 Front view of PCM




Figure 8 Back view of PCM

